



ПЛАСТИНЫ

Примеры поставок пьезокерамических пластин

a – длина, b – ширина, h – высота,

f_a и f_p – частоты антирезонанса и резонанса соответственно

$a \times b$, mm	h , mm	f_a ; f_p , кГц
3,0x4,0	0,4	f_a 5225÷5775
4,0x4,0	0,2	f_a 10450÷11550
4,0x4,0	0,4	f_a 5225÷5775
4,0x6,0	0,4	f_a 5225÷5775
4,0x4,0	0,9	f_a 2479÷2730
5,0x5,0	0,34	-
5,0x5,0	0,37	-
5,0x5,0	0,4	-
5,0x4,0	0,2	f_a 10450÷11550
5,5x2,1	0,13	f_a 15200÷16800
5,5x2,1	0,14	f_a 1853÷2047
5,0x10,0	0,4	f_a 5225÷5775
5,0x12,0	0,4	f_a 5225÷5775
7,0x6,0	0,4	f_p 4750÷5250
7,5x1,5	0,5	-
9,0x9,0	0,37	-
10,0x1,0	0,8	f_a 2558÷2942
10,0x1,3	0,37	-
10,0x2,0	0,5	-
10,0x2,0	0,8	f_a 2558÷2942
10,0x6,0	0,8	f_p 2375÷2625
10,0x13,0	0,7	f_a 2613÷2887
10,0x35,0	0,9	f_a 2470÷2730
11,0x9,0	0,4	f_p 4750÷5250
11,0x11,0	1	-
12,0x5,0	0,4	f_p 2375÷2625

Пластины пьезокерамические

a x b, mm	h, mm	f_a; f_p, кГц
12,0x8,0	0,6	f _p 2850÷3150
12,0x5,0	0,8	f _a 2565÷2835
12,0x8,0	1,1	f _a 1900÷2100
12,0x10,0	0,8	f _a 2375÷2625
12,0x16,0	0,7	f _a 2613÷2887
12,0x16,0	1	f _a 1853÷2047
12,0x16,0	1,4	f _a 1235÷1365
12,0x24,0	0,7	f _a 2613÷2887
12,0x24,0	1,4	f _a 1235÷1365
12,0x12,0	0,8	f _p 2375÷2625
14,0x8,0	1,56	f _p 1185÷1315
14,0x11,0	1	f _p 1710÷1890
14,0x11,0	1,6	f _p 1185÷1315
16,0x8,0	0,8	f _p 2375÷2625
16,0x8,0	0,8	f _a 2375÷2625
17,0x10,0	1,4	—
20,0x5,0	0,4	f _p 4750÷5250
20,0x5,0	0,8	f _p 2375÷2625
20,0x10,0	1	f _p 1710÷1890
20,0x12,0	0,55	f _p 2375÷2625
24,0x8,0	1	—
25,0x11,0	0,8	f _p 2375÷2625
25,0x25,0	0,4	f _a 4750÷5250
25,0x25,0	0,8	f _p 2375÷2625
25,0x25,0	0,8	f _p 2375÷2625
28,0x20,0	0,8	f _p 2375÷2625
28,0x20,0	1	f _p 1710÷1890
29,0x17,0	0,36	—
29,0x17,0	0,7	—
29,0x17,0	1,1	—
29,0x17,0	1,6	—
29,0x17,0	3	—
29,0x17,0	4	—
29,0x17,0	7	—
31,0x21,0	0,72	—
31,0x21,0	1	—
31,0x21,0	3	—

Пластины пьезокерамические

a x b, mm	h, mm	f_a; f_p, кГц
31,0x21,0	3	—
31,0x21,0	4	—
31,0x21,0	5	—
31,0x21,0	6	—
31,0x21,0	7	—
40,0x10,0	0,3	—
40,0x10,0	0,4	—
40,0x10,0	0,5	—
40,0x12,0	0,5	f _a 2185÷2415
40,0x12,0	1	f _a 2185÷2415
40,0x20,0	0,4	—
50,0x4,0	3	—
50,0x5,0	0,3	f _p 3300÷3600
50,0x10,0	5	—
50,0x30,0	0,4	f _p 4750÷5250
50,0x30,0	0,8	f _p 2375÷2625